

Tamkeen Modern Pipes Company

Jeddah - 2nd Industrial Are

P.O. box-15442, Jeddah-21543 KSA

Phone No:012-6110657, Fax:012-61106

Email:info@tamkeen.com.sa

Website:www.tamkeen.com.sa




2022-02-23 T10:30:29

Test report

Test-Id 2022020020/000

Set pressure	12.60 bar	Hoop stress (sigma)	12.49 N/mm ²
min. Pressure	12.35 bar	Wall thickness	3.60 mm
max. Pressure	12.85 bar	Outer diameter	75.00 mm
Conditioning time	3.00 ih	Lab operator	Anis
Set temperature	20.0 °C		
Start date	09-Feb-22 04:33:25 PM		
Timecounter start	0.00 ih		
End date	23-Mar-22 09:59:42 AM		
Time counter	1,000.00 ih		
Pressurize time	71.00 SEC		

Record:



Events: Start date End date Description