

Tamkeen Modern Pipes Company

Jeddah - 2nd Industrial Are

P.O. box-15442, Jeddah-21543 KSA

Phone No:012-6110657, Fax:012-61106

Email:info@tamkeen.com.sa

Website:www.tamkeen.com.sa




2022-03-27 T02:01:13

Test report

Test-Id 2022020027/000

Set pressure	20.15 bar	Hoop stress (sigma)	12.50 N/mm ²
min. Pressure	19.75 bar	Wall thickness	4.70 mm
max. Pressure	20.55 bar	Outer diameter	63.00 mm
Conditioning time	3.00 ih	Lab operator	Anis
Set temperature	20.0 °C		
Start date	13-Feb-22 10:31:13 AM		
Timecounter start	0.00 ih		
End date	27-Mar-22 04:01:13 AM		
Time counter	1,000.00 ih		
Pressurize time	83.00 SEC		

Record:



Events: **Start date** **End date** **Description**