

Tamkeen Modern Pipes Company

Jeddah - 2nd Industrial Are

P.O. box-15442, Jeddah-21543 KSA

Phone No:012-6110657, Fax:012-61106

Email:info@tamkeen.com.sa

Website:www.tamkeen.com.sa




2022-04-18 T13:24:14

Test report

Test-Id 2022030030/000

Set pressure	20.00 bar	Hoop stress (sigma)	12.43 N/mm ²
min. Pressure	19.60 bar	Wall thickness	6.70 mm
max. Pressure	20.40 bar	Outer diameter	90.00 mm
Conditioning time	3.00 ih	Lab operator	Anis
Set temperature	60.0 °C		
Start date	07-Mar-22 07:15:22 PM		
Timecounter start	0.00 ih		
End date	18-Apr-22 12:45:26 PM		
Time counter	1,000.00 ih		
Pressurize time	32.00 SEC		

Record:



Events: **Start date** **End date** **Description**